



constructive solutions

Renderoc® CS

Single part, non shrink, cementitious, crack sealer for plaster, masonry and concrete

Uses

Renderoc CS is used for sealing cracks on plaster, masonry and concrete substrates.

Advantages

- Single component - Easy to use
- Versatile - Can be used for plaster, masonry or concrete, can be painted after application
- Non sagging - Can be used for horizontal, vertical and overhead applications
- Good adhesion - Effective bonding with substrate
- Non Shrink - Shrinkage cracking eliminated

Description

Renderoc CS is a crack sealing cementitious material in powder form. It is easy to apply and can be finished or smoothened off with a putty blade or a damp sponge. It sets quickly on application and can be over coated with common paints / coatings.

Properties

Colour	White
Setting time	15 to 20 min
Compressive strength (ASTMC109)	22 N/mm ² in 7 days and 24 N/mm ² in 28 days
Fresh wet density	1.85 - 1.90g/cc
W/p Ratio	0.36
Mix proportions by volume	1 part water : 2.5 -3 parts of powder
Minimum application temperature	10°C

Application instructions

Surface Preparation

The cracks to be sealed shall be saw cut or chiselled to form a 'V' groove of approximately of 6mm x 6mm. The grooves shall be cleaned to remove all the loose particles, dust, etc.

The groove shall be sprinkled with clean water before applying the sealing mortar.

Mixing

Renderoc CS shall be mixed with water adopting w/p ratio 0.36 by weight or a mix proportion of 1 part of water to 2.5 - 3.0 parts of Renderoc CS, by volume. Thorough mixing shall be carried out till a smooth, homogenous paste is obtained.

Application

The mixed paste is filled into the groove by gloved hand and the surface finished using a putty blade. This is continued till the full length of crack is sealed.

Curing

Curing is necessary only when groove size exceeds 6mm width or in areas exposed to UV.

Cleaning

Tools may be cleaned with clean water as Renderoc CS is a cement based product.

Limitations

Renderoc CS crack sealer cannot be used for moving cracks and for crack width greater than 30mm.

Estimating

Packaging

Renderoc CS is supplied in 1kg. packs.

Coverage

30 RM for a V groove crack of 6mm x 6mm. The actual coverage may vary depending on the substrate conditions.

Storage

Shelf life

Renderoc CS has a shelf life of 12 months in original unopened packs if stored in unopened conditions below 35°C.

Precaution

Health & Safety instructions

Renderoc CS has no health hazards in normal use. Gloves shall be worn while mixing and during application. Splashes of material to the eyes shall be washed off with clean water. In the event of prolonged irritation, medical advice shall be sought.

Renderoc[®] CS

Fire

Renderoc CS is non flammable.

Additional information

Fosroc manufactures a wide range of products pecifically designed for the repair and refurbishment of damaged reinforced concrete. These include hand placed and trowellable repair mortars, fluid micro concretes, chemical resistant epoxy mortars and a comprehensive package of protective coatings. In addition, a wide range of complimentary products are available. These include admixtures, joint sealants, waterproofing membranes, grouting, anchoring, and specialised flooring materials.

Separate datasheets are available on these products

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by



MATT INDIA CO

G-25, SECTOR -63,
GAUTAM BUDDH NAGAR,
UP-201307 INDIA

Phone No:

09555666476

09555655544

Email: mattindia1@gmail.com